

# SABIC<sup>®</sup> PP 620P

POLYPROPYLENE RANDOM COPOLYMER

## DESCRIPTION

PP 620P is a general-purpose random PP grade primarily produced for extrusion applications. Due to its basic design, it can be used in a wide range of applications. With the well balance mechanical properties and easy extrusion behavior, it is highly useful in a wide range of applications.

## TYPICAL APPLICATIONS

Typical applications are: extrusion blow molding, sheet extrusion and other extrusion applications.

## TYPICAL PROPERTY VALUES

Revision 20181012

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
<b>Melt Flow Rate</b>			
at 230 °C and 2.16 kg	1.7	dg/min	ISO 1133
<b>Density</b>	905	kg/m <sup>3</sup>	ASTM D1505
<b>Molecular Weight Distribution</b>	Broad	-	-
<b>Isotacticity</b>	Medium	-	-
<b>MECHANICAL PROPERTIES</b>			
<b>Tensile test</b>			
tensile modulus <sup>(1)</sup>	850	MPa	ISO 527-2 1A
stress at yield	25	MPa	ISO 527-2 1A
strain at yield <sup>(2)</sup>	12	%	ISO 527-2 1A
<b>Izod impact notched</b>			
at 23 °C	8.0	kJ/m <sup>2</sup>	ISO 180/1A
<b>Charpy Impact Strength Notched</b>			
at 23 °C	8.0	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Hardness Shore D</b>	60	-	ISO 868
<b>THERMAL PROPERTIES</b>			
<b>Vicat Softening Temperature <sup>(3)</sup></b>			
at 10 N (VST/A)	128	°C	ISO 306
at 50 N (VST/B)	63	°C	ISO 306

(1) Speed of testing: 1 mm/min

(2) Speed of testing: 50 mm/min

(3) Temperature rate: 120°C/h

## HEALTH, SAFETY AND FOOD CONTACT REGULATIONS

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.SABIC.com>. For additional specific information please contact SABIC local representative.

## QUALITY

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.



## STORAGE AND HANDLING

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.